

Application No.: 10/000284

Case No.: 56530US002


**Amendments to the Claims:**

The following Listing of Claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims**

1. (Currently Amended) An ink comprising an aqueous vehicle and dispersed particles of a silyl-terminated sulfopoly(ester-urethane), wherein the ink has a viscosity of less than about 20 mPa.s at 20°C and at a shear rate of 1000 s<sup>-1</sup> and said ink is an ink jet ink.

2. (Previously Presented) The ink of claim 1, wherein the silyl-terminated sulfopoly(ester-urethane) is described by the formula:




wherein

R represents a trivalent C<sub>6</sub> - C<sub>12</sub> aryl group or a trivalent C<sub>1</sub> - C<sub>20</sub> aliphatic group wherein M is H<sup>+</sup>, an alkali metal cation, an alkaline earth metal cation, or a primary, secondary, tertiary, or quaternary ammonium cation;

each m independently represents 0 or 1, each n independently represents 0 or 1, each s independently represents 0 or 1, with the proviso that, at least one of m or n must be equal to 1;

each R<sup>D</sup> independently represents:

1) at least one of a divalent linear or branched organic group of 20 to 150 carbon atoms in units of 2 to 12 methylene groups and arylene groups of 6 to 10 carbon atoms separated by at least one of 1 to 50 catenary oxygen atoms and by 1 to 30 oxycarbonyl groups,



2) an organic group selected from the group consisting of a linear or branched alkylene group having 2 to 12 carbon atoms, a cyclopentamethylene group, a cyclohexamethylene group, a 5- or 6-membered azacyclic group, a phenylene group, a naphthalene group, a

Application No.: 10/000284


Case No.: 56530US002

phenylenemethylenephenylene group, the organic group optionally being substituted by up to four lower alkyl groups having 1 to 4 carbon atoms and a total of up to 15 carbon atoms, which organic group can be chain extended by a transesterification reaction between a diol terminated ester precursor and a lower aliphatic diester of an aliphatic diacid having from 2 to 12 carbons or an aromatic diacid having from 8 to 12 carbons or reaction between a diol terminated ester precursor and an aliphatic lactone of 4 to 6 carbons, or

3) the structure  $\{-R^1(X^1-R^2-X^1-R^1)_p-\}$  where  $p$  is an integer from 1 to 5, produced by the reaction of a polyol with an isocyanate having the structure  $OCN-R^2-NCO$  to produce a segment having a molecular weight of from 500 to 4,000;


each  $R^1$  independently represents a linear or branched alkylene group having 2 to 12 carbon atoms, or an arylene group having 6 to 10 carbon atoms;

each  $X^1$  independently represents



each  $R^2$  independently represents an organic group selected from the group consisting of a linear or branched alkylene group having 2 to 12 carbon atoms, a cyclopentamethylene group, a cyclohexamethylene group, a 5- or 6-membered azacyclic group, a phenylene group, a naphthalene group, a phenylenemethylenephenylene group, the organic group optionally being substituted by up to four lower alkyl groups having 1 to 4 carbon atoms and a total of at most 15 carbon atoms;

each  $X^2$  independently represents




Application No.: 10/000284


Case No.: 56530US002

wherein each  $R^A$  independently represents hydrogen, lower alkyl having 1 to 4 carbon atoms, or  $R^1-Y$ ;


each  $R^H$  independently represents a divalent hydrophobic group selected from divalent oligomeric siloxanes having the structure



divalent organic groups having the structure




or divalent organic groups having one of the structures



or quaternary salts thereof, wherein

each  $R^3$  independently represents a divalent linear or branched alkylene group having 2 to 12 carbon atoms, or a divalent arylene or alkarylene group having 6 to 20 carbon atoms;


each  $Y$  independently represents H, an alkyl group having from 1 to 20 carbon atoms, an aryl group having from 6 to 10 carbon atoms, or



wherein each  $R^4$  independently represents a monovalent lower alkyl group having from 1 to 4 carbon atoms, each  $R^8$  is H or a monovalent lower alkyl group having from 1 to 4 carbon atoms, each  $z$  is independently 2 or 3, each  $w$  is independently 0 or 1, and wherein  $z + w = 3$ , with the proviso that at least one  $Y$  has the formula

Application No.: 10/000284


Case No.: 56530US002




each  $\text{R}^5$  independently represents a monovalent group selected from the group consisting of alkyl groups of 1 to 12 carbon atoms, aryl having 6 to 10 carbon atoms, or aralkyl groups having 6 to 10 carbon atoms, with at least 70 percent of  $\text{R}^4$  being methyl;

each  $g$  independently represents an integer of from 10 to 300;

each  $\text{X}^3$  independently represents a covalent bond, a carbonyl group,



or a divalent amido group



each  $\text{R}^6$  independently represents a monovalent group selected from the group consisting of alkyl groups of about 4 to about 60 carbon atoms;

each  $\text{R}^7$  independently represents a divalent group selected from the group consisting of alkylene groups of 2 to about 12 carbon atoms; and

each  $\text{R}_f$  independently represents a monovalent saturated fluoroaliphatic group having 6 to 12 carbon atoms, at least four of which are fully-fluorinated carbon atoms.

3. (Previously Presented) The ink of claim 1, wherein the ink is free of organic solvents.

4. (Previously Presented) The ink of claim 1, further comprising a colorant, wherein the colorant is a pigment.

5. (Previously Presented) The ink of claim 1, further comprising a colorant, wherein the colorant is a dye.

6. (Previously Presented) The ink of claim 1, further comprising an additional dispersed polymer.

Application No.: 10/000284

Case No.: 56530US002

7. (Previously Presented) The ink of claim 6, wherein the additional dispersed polymer is present in an amount of from about 0.1 to about 3 times the weight of the silyl-terminated sulfopoly(ester-urethane) polymer.

8. (Previously Presented) The ink of claim 7, wherein the additional dispersed polymer is an acrylic polymer.

9. (Previously Presented) The ink of claim 1, further comprising a humectant.

10. (Previously Presented) The ink of claim 1, wherein the ink has a solids content of at least 20 weight percent of the total ink composition.


11. (Previously Presented) The ink of claim 1, wherein the ink has a solids content of at least 30 weight percent of the total ink composition.

12. (Previously Presented) The ink of claim 1, wherein the ink has a solids content of at least 50 weight percent of the total ink composition.


13. Cancelled

14. (Previously Presented) The ink of claim 1, wherein the ink has a viscosity of less than about 5 mPa·s at 20 °C and at a shear rate of 1000 s<sup>-1</sup>.

15. (Previously Presented) The ink of claim 2, wherein



is:



19. (Previously Presented) The ink set of claim 17, further comprising a fourth blendable ink.

Application No.: 10/000284

Case No.: 56530US002

20. (Previously Presented) The ink set of claim 19, wherein the fourth blendable ink is a black ink.

21. (Previously Presented) The ink set of claim 19, further comprising a fifth blendable ink.

22. (Previously Presented) The ink set of claim 21, wherein the fifth blendable ink is a white ink.

23. (Previously Presented) The ink of claim 1, wherein the ink is contained within an ink jet printer cartridge.

24-52. Cancelled